

High Durability Powder Coating			
<b>Product Code:</b>		272 Line	
<b>Specification met:</b>		Meets and/or exceeds requirements of AS3715, BS6496.	
<b>Description</b>			
Duralloy® is a TGIC free, tough thermosetting powder coating that exhibits decorative and durability characteristics suitable for interior and exterior product applications combined with excellent overall performance.			
<b>Features</b>		<b>Benefits</b>	
7 year Film Integrity Warranty*		Guaranteed performance on correctly pre-treated aluminium	
7 year Colour Warranty*		Very good colour retention	
Low cure		Cost savings on energy or increased line speeds	
Wide product range		Extensive selection of colours	
No solvents or emissions		Less waste and pollution to the environment	
* Warranties are only available when application is completed by Dulux Registered Applicators using correctly pretreated Extruded Aluminium. For full details and conditions, including limitations, refer to Duralloy Performance Warranty.			
<b>Uses</b>			
Duralloy® was developed primarily for use on extruded aluminium, including window and door joinery, and extruded aluminium panel work on residential and light commercial buildings. Duralloy® may however be used in many applications over a variety of substrates, including steel and aluminium.			
<b>Performance Guide</b>			
<b>Weather</b>	Very good resistance to weathering.	<b>Salt Spray</b>	Excellent salt spray resistance over pre-treated alum. (3000 hours ASTM B117)
<b>Heat</b>	Excellent resistance to 120°C continuous service conditions.	<b>Humidity</b>	Excellent resistance to 38°C/100% humidity for 1000 hours on pre-treated aluminium.
<b>Acid</b>	Resistant to spills of dilute acid. Avoid contact.	<b>Abrasion</b>	Very good resistance to abrasion.
<b>Alkali</b>	Resistant to spills of dilute alkali. Avoid contact.	<b>Pencil Hardness</b>	Min F
		<b>Knoops Hardness</b>	Min 15
<b>Flexibility</b>	Limited < or = 80 inch/lb Avoid post fabrication or refer to applicator's manual for further details	<b>Cross Hatch Adhesion</b>	No removal
<b>Chemical Resistance</b>			
<b>Mortar</b>	Resistant	<b>White Spirits</b>	Resistant
<b>Ethanol</b>	Resistant	<b>Xylene</b>	Slight softening/limit contact
<b>Methyl Ethyl Ketone</b>	Softens/avoid contact	<b>Ethyl Acetate</b>	Softens/avoid contact
<b>Product Guide</b>			
<b>Colour</b>	A good range ex Australia	<b>Specific gravity</b>	1.2 - 1.7 @ colour

# Duralloy®

<b>Gloss Level</b>	30 - 98% at 60°,	<b>Shelf life</b>	12 months when stored <25°C/dry
--------------------	------------------	-------------------	---------------------------------

## Application Data

<b>Application Method</b>	Electrostatic spray.		
<b>Clean Up</b>	Dust or vacuum loose powder. Avoid use of compressed air.		
<b>Cure Schedule</b>	<b>Metal Temperature (°C)</b>	<b>Time (minutes)</b>	
	210	4	
	200	5	
	180	8	
<b>Cured Film Thickness</b>	Recommended:	80 µm	
	Range:	50 – 120 µm	

Note: Light colours may require a higher minimum film build for optimum coverage and colour consistency.

### Theoretical spreading rate at recommended film thickness

A coverage rate of 8 - 10m<sup>2</sup>/kg corresponds to 80 µm cured film thickness assuming no loss. Practical spreading rates will vary due to such factors as method and conditions of application and surface profile and texture.

## Application Guide

### Surface Preparation

Surfaces should be prepared according to AS1627.6-2003 Section 3 to achieve a conversion coating corresponding to Class 1. Chemical supplier recommendations should also be adhered to, as appropriate. Suitable pre-treatment includes:

Aluminium	Chrome chromate or green chromate/phosphate	(refer AS1627.6-2003)
Ferrous metals	Abrasive blast(SA 2.5)/Zincshield™ powder primer, Or Zinc phosphate or Iron phosphate	(refer Zincshield™ Data Sheet) (refer BS6497)
Zinc Coated Steels (eg. Galvanising)	Zinc Phosphate or chromate	(refer BS6497)
Stainless Steel	Suitable metal blast. Recommended maximum blast profile of 25µm	

### Application Procedure and Equipment

1a)	For fluidised bed, ensure uniform fluidisation of powder. Fluidised powder should resemble “simmering liquid”. Aged or compacted powder may require pre-conditioning for several minutes to fluidise evenly.
1b)	For box feeders, ensure probe is fully inserted in powder and operated as per manufacturer’s recommendations. Box feeders are not suitable for the application of pearlescent and metallic finishes
2.	Apply by electrostatic spray.
3.	Cure as per recommendations outlined above.
	Metal temperatures in excess of 210°C should be avoided due to the possibility of colour change or thermal degradation of the polymer.
4.	Test for cure of the coating by contact with a drop of Corsol PGMA (available from Dulux Powder Coatings) for 30 seconds. Surface should be wiped dry and immediately checked for softening. Only slight surface softening should occur.

## Care and Maintenance

As a general rule, cleaning of externally located powder coating surfaces must take place every six months. Where salts/pollutants are more prevalent such as seaside, industrial and geothermal areas, a cleaning program should be carried out more frequently.

### THREE STEPS TO CLEANING POWDER COATED SURFACES

1. Remove loose deposits with a wet sponge (avoid scratching the surface by dry dusting).
2. Using a soft clean cloth and a mild detergent in warm water, clean the powder coating to remove dust, salt or other deposits.
3. Always rinse after cleaning with fresh water to remove any remaining detergent.

**WARNING:** In some cases, strong solvents recommended for thinning various types of paints and also for cleaning up mastics/sealants are harmful to the extended life of the powder coated surface. These solvents should not be used for cleaning purposes and will render the warranty void if used. If paint splashes or sealants/mastics need to be removed then the following solvents can be used safely: Methylated Spirits, Ethyl Alcohol, Isopropanol.

# Duralloy®

<b>Health and Safety</b>			
<p>The MSDS is an integral part of using this product as it contains information on the potential health effect of exposure, personal protective equipment needed and other relevant SH&amp;E information.</p> <p>For detailed information, refer to product label and the current Chemical Data Sheet (No. 10489) available through Sales and Customer Service.</p>			
Phone: Australia:-	13 24 99	New Zealand:-	09 441 8244.
<b>Precautions and Limitations</b>			
<ul style="list-style-type: none"> <li>Duralloy® is only available in colours which meet Dulux Powder Coatings pigmentation criteria. Strong, bold colours may not necessarily meet these criteria and should be referred to Dulux Powder Coatings before specifying.</li> <li>As a result of possible wide application variations and stoving conditions, some products and colours may show variation between Dulux Powder Coatings prepared samples and production applied material. Therefore, it is the applicator and/or their customer's responsibility to ensure the product conforms to their requirements.</li> <li>For optimum performance ensure recommended dry film thickness is obtained.</li> <li>Not recommended for use in highly corrosive environments such as severe marine or industrial locations.</li> <li>Not recommended for components which are exposed to constant temperatures exceeding 120°C.</li> </ul>			
<ul style="list-style-type: none"> <li>Excessive bending or post fabrication may cause cracking of the pretreatment and powder coating. Specifiers are advised to discuss post fabrication techniques with Dulux or the Registered Applicator prior to commencing such fabrication</li> </ul>			
<ul style="list-style-type: none"> <li>Please refer to the Duralloy Performance Warranty for conditions &amp; limitations which effect the warranties described in this data sheet.</li> </ul>			
<b>Transport and Storage</b>			
<b>Sizes:</b>	20 kg	<b>Flashpoint:</b>	Not Applicable
<b>Weight:</b>	20 kg	<b>UN:</b>	Not Applicable
<b>Dangerous Goods Class:</b>	Not Applicable	<b>Package Group:</b>	Not Applicable
<b>Shipment Name:</b>	Not dangerous goods. No special transport requirements.		
	Dulux Powder & Industrial Coatings	Dulux Powder & Industrial Coatings	
	1-15 Pound Road	31B Hillside Road	
	Dandenong South, VIC 3175	Glenfield, Auckland	
	Australia	New Zealand	
	ACN 004 117 828		
<b>Telephone:</b>	61 3 8787 4500	64 9 441 8244	
<b>Fax:</b>	61 3 8787 4542	64 9 441 8242	
Dulux and Other marks followed by ® are registered trademarks. Marks followed by the symbol ™ are trademarks.			
<p><b>DISCLAIMER:</b> Any advice, recommendation, information, assistance or service provided by Dulux Powder Coatings in relation to goods manufactured by it or their use and application is given in good faith and is believed by Dulux Powder Coatings to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by Dulux Powder Coatings provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon Dulux Powder Coatings by any condition or warranty implied by applicable legislation, regulation or other Government ordinance voiding or prohibiting such exclusion, limitation or modification</p>			